

# RHEOCOLOR® L

## Liquid Coloring Admixtures

### Description

RHEOCOLOR L liquid coloring admixtures are patented, engineered, high quality coloring dispersions producing enhanced decorative concrete. RHEOCOLOR L liquid coloring admixtures are ready-to-use integral liquids that come in four base colors:

- Black
- Light Red
- Medium Red
- Yellow

The four base colors can be used to make a wide range of colors including but not limited to the colors depicted on the BASF Construction Chemicals Color Selector Card.

### Applications

Recommended for use in:

- Integrally colored decorative concrete
- Imprinted concrete
- Ready mixed concrete
- Manufactured concrete products
- Stone veneer products
- Precast concrete
- Pervious concrete
- Self-consolidating concrete

### Features

- Liquid coloring admixtures formulated for the automated CAM (Coloring Admixture Measuring) System
- Used with BASF Construction Chemicals performance admixtures in the production of durable decorative concrete
- Faster dispersion into concrete

### Benefits

- Beautiful, long-lasting integrally colored concrete
- Enhanced finishing characteristics
- Color vibrancy
- Excellent color accuracy
- Batch-to-batch color consistency and verifiable color batching results
- Increased productivity and reduced labor
- Clean and simple batching
- Quality custom color services
- Single source producer support for chemical, mineral and coloring admixtures

RHEOCOLOR L liquid coloring admixtures meet the colorfastness testing of 500 hours light exposure per ASTM C 979. In addition, RHEOCOLOR L liquid coloring admixtures have successfully completed 1500 hours of aggressive Xenon Arc testing per ASTM G 155.

**Typical Properties :** Density 14-16 lb/gal(1.68-1.92 kg/L) [@72 °F (22 °C)]

### Guidelines for Use

**General:** Due to the graying effect of most cements, there are some custom colors that can only be produced using very light or white cements. Variations in water content, cement type, color variations in cementitious materials or aggregates, finish texture, timing of operations, curing or forming methods, release agents or surface treatments may produce distinct, though in many cases slight, variations in final color. All standard color matches are completed using a medium shade of portland cement.

**Dosage:** RHEOCOLOR L color formulas for standard and other regional colors are programmed into the CAM System upon installation.

RHEOCOLOR L admixture is water neutral at loading rates of 5% or less. At loading rates greater than 5%, RHEOCOLOR L may provide increased water reduction depending on local concrete materials. Therefore, at loading rates above 5%, laboratory/field evaluations of RHEOCOLOR L admixture are recommended to verify desired concrete performance.

**Mixing:** With the automated CAM System, RHEOCOLOR L liquid coloring admixtures is weighed or metered and dispensed prior to or while loading concrete. Product and rinse water are calculated by the CAM System and should be included as total batch water. For best results add coloring admixtures prior to batching concrete. For post addition, mix a minimum of 4-5 minutes at normal mixing speed to assure uniformity.

For best results, truck or mixer should be clean and pre-wet with no standing water. A minimum batch size equal to 1/3 of the mixer capacity should be used as a guideline for efficient mixing. Keeping the addition order, mixing time, materials and water cement ratio constant between multiple batches is critical for color consistency.

# Product Data: RHEOCOLOR® L

**Concrete Placement and Finishing:** Final color and textures should be pre-approved with a cured jobsite mock up. In accordance with proper construction practices, slabs on grade shall be placed over properly compacted and prepared subgrade. Spade formed edges and consolidate and strike off surface as normal. Care should be taken to avoid over-vibration, over-working and over-finishing, or other practices that might cause excessive bleeding or significantly increase the surface mortar content.

Trowelling or broom-finishing decorative concrete should be performed in the same direction to maintain uniform appearance. Do not add additional water to the concrete either by retempering or by adding water to the surface during the finishing process.

**Curing:** Proper curing of decorative concrete is required to enhance the depth of color, provide a more uniformly colored concrete, and provide surface protection. Kure 1315 water-based curing and sealing compound from BASF is recommended or a compatible curing and sealing compound.

*Note: Until decorative concrete is fully cured, the color may appear darker than expected. Curing with burlap, plastic sheeting, water or other curing compounds may be detrimental to color uniformity and is not recommended. For more information on curing decorative concrete contact your local sales representative.*

**Maintenance:** Regular cleaning of decorative concrete is recommended. In general, resealing may be desired periodically as the sealed surface wears. Maintenance applications will be accelerated in areas of heavy use or frequent or aggressive cleaning. Heavily soiled interior areas may be cleaned by wet mopping or scrubbing with a stiff-bristle brush and properly diluted, high-quality commercial detergent. For large areas, automatic scrubbers may be more efficient and cost effective.

**Clean-Up:** RHEOCOLOR L liquid coloring admixtures are water based and can be cleaned with soap and water.

## Product Notes

### **Corrosivity – Non-Chloride, Non-Corrosive:**

RHEOCOLOR L liquid coloring admixtures will neither initiate nor promote corrosion of reinforcing steel embedded in concrete. No calcium chloride or chloride-based ingredients are used in the manufacture of these products. Complete safety information can be found on the RHEOCOLOR L Material Safety Data Sheets.

**Compatibility:** RHEOCOLOR L liquid coloring admixtures are compatible with most admixtures used in the production of quality concrete. Mineral additives may affect color and should be checked for potential adjustments. All other admixtures should be dispensed into the concrete separately. The use of calcium chloride accelerators are not recommended in decorative concrete. Final color and texture should be verified with a cured jobsite mock-up.

## Storage and Handling

**Storage Temperature:** RHEOCOLOR L liquid coloring admixtures should be stored between 40-100 °F (4-38 °C) with regular mixing or recirculation. Always mix material prior to use. Automated recirculation is included with the CAM System. If RHEOCOLOR L liquid coloring admixtures freeze, contact your local sales representative.

**Shelf Life:** RHEOCOLOR L liquid coloring admixtures have a minimum shelf life of 12 months if properly stored (see handling and storage requirements above).

## Packaging

RHEOCOLOR L liquid coloring admixtures are available in 3350 lb (1520 kg) net returnable totes.

## Related Documents

RHEOCOLOR L Material Safety Data Sheets:

- Black
- Light Red
- Medium Red
- Yellow

## Additional Information

For additional information on RHEOCOLOR L liquid coloring admixtures, contact your local sales representative.

*The Admixture Systems business of BASF Construction Chemicals is a leading provider of innovative admixtures for specialty concrete used in the ready mix, precast, manufactured concrete products, underground construction and paving markets throughout the North American region. The Company's respected Master Builders brand products are used to improve the placing, pumping, finishing, appearance and performance characteristics of concrete.*

LIMITED WARRANTY NOTICE. We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claims regarding product defect must be received in writing within one (1) year from the date of shipment. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments.

**For Professional use only. Not for sale to or use by the general public.**

**BASF Construction Chemicals**  
Admixture Systems

[www.masterbuilders.com](http://www.masterbuilders.com)

United States 23700 Chagrin Boulevard, Cleveland, Ohio 44122-5544 ● Tel: 800 628-9990 ● Fax: 216 839-8821  
Canada 1800 Clark Boulevard, Brampton, Ontario L6T 4M7 ● Tel: 800 387-5862 ● Fax: 905 792-0651

© Construction Research & Technology GMBH

© BASF Construction Chemicals, 2008 ● Printed in USA ● 04/09 ● LIT # 2000068

**Master  
Builders**