

PRODUCT DATA

3 03 37 13 Shotcrete

SHOTPATCH® 21

Silica-fume-enhanced structural wet- or dry-process shotcrete

Description

Shotpatch® 21 is prepackaged, silica-fume-enhanced mortar containing an integral corrosion inhibitor. It exhibits high bond strengths, low permeability, and excellent resistance to freeze/thaw cycling and salt scaling. Its unique technology permits application by wet or dry shotcrete processes.

Yield

Approximately 0.46 ft³ (0.013 m³), which will cover approximately 5.5 ft² (0.51 m²) at a 1" (25 mm) depth, excluding rebound and waste.

Packaging

55 lb (25 kg) multi-wall bags
3,300 lb (1,500 kg) bulk bags

Shelf Life

1 year when properly stored

Storage

Store in unopened bags in clean, dry conditions from 45 to 90° F (7 to 32° C).

Features

- Versatile
- One component
- Low permeability
- Contains an integral corrosion inhibitor
- Cohesive
- Workable
- Prepackaged quality

Benefits

- Designed for dry or wet shotcrete processes
- Requires only the addition of potable water; reduces handling
- Resists water and chloride-ion penetration
- Prevents corrosion from a wide range of sources and environments
- High build and reduced rebound
- Easy to cut and finish
- Bag-to-bag uniformity

Where to Use

APPLICATION

- Structural repair and retrofit of
 - Bridges, tunnels, and parking garages
 - Piers, docks, and dams
 - Reservoirs and tanks
 - Treatment facilities
 - Canals and aqueducts

LOCATION

- Horizontal, vertical, and overhead surfaces
- Interior or exterior

How to Apply**Surface Preparation**

CONCRETE

1. Perform surface preparation in compliance with ICRI Technical Guideline No. 03730 "Guideline for Surface Preparation for the Repair of Deteriorated Concrete Resulting from Reinforcing Steel Corrosion" and ACI 506.2 "Specification for Materials, Proportioning, and Application of Shotcrete."
2. Remove all unsound or delaminated concrete, providing a minimum 1/4" (6 mm) substrate-profile amplitude and 3/4" (19 mm) clearance behind corroded reinforcing steel.
3. Sawcut the area being repaired to a minimum depth of 1/4" (6 mm).
4. After removing concrete, mechanically abrade the surface to remove all bond-inhibiting materials and provide additional mechanical bond. Do not use a method of surface preparation that will fracture the concrete. Verify the absence of microcracking or bruising in accordance with ICRI Guideline No. 03732.
5. Presoak the prepared concrete surface to provide a saturated surface-dry (SSD) condition.

Technical Data

Composition

Shotpatch® 21 is a one-component silica-fume-enhanced mortar containing an integral corrosion inhibitor.

Compliances

- Cement meets ASTM C 150 standards
- Sand gradation meets ASTM C 33 and ACI 506 standards

Typical Properties

PROPERTY	VALUE
Unit weight , lb/ft ³ (kg/m ³)	134 (2,147)
Set times , hrs:min (ASTM C 266)	
Initial set	1:40
Final set	4:25

Test Data

PROPERTY	RESULTS			TEST METHODS
	1 day Psi (MPa)	7 day Psi (MPa)	28 day Psi (MPa)	
Compressive strength	2,500 (17.2)	6,000 (41.4)	7,000 (48.3)	ASTM C 109
Splitting tensile strength	240 (1.6)	400 (2.7)	490 (3.3)	ASTM C 496
Flexural strength	700 (4.8)	1,200 (8.3)	1,800 (12.4)	ASTM C 348
Direct tensile bond strength	160 (1.1)	210 (1.2)	230 (1.5)	ACI 503R, Appendix A
Slant shear bond strength (8.3)	1,200 (17.2)	2,500 (20.7)	3,000	ASTM C 882, modified ¹
Compressive strength				ASTM C 42
	3 day psi (MPa)	28 day psi (MPa)		
Dry process	6,000 (41.4)	10,000 (69.0)		
Wet process	5,000 (34.5)	9,000 (62.0)		
Drying shrinkage , %, at 28 days	0.10			ASTM C 157, modified ²
Modulus of elasticity , psi (GPa), at 28 days	4.9 x 10 ⁶ (33.8)			ASTM C 469
Rapid chloride permeability , coulombs, at 28 days	740 (very low)			ASTM C 1202 / AASHTO T-277
Freeze/thaw resistance , % RDM, at 300 cycles	97			ASTM C 666, Procedure A

¹No epoxy bonding agent used.

²ICRI Guideline #03733, 1 by 1 by 10" (25 by 25 by 250 mm) prism, air cured.

Results were obtained when material was mixed with 0.72 gallons (2.7 L) of water per bag and cured at 73° F (22° C). Expect reasonable variations, depending upon application methods, test methods, and curing conditions.

CORRODED REINFORCING STEEL

1. Remove all oxidation and scale from the exposed reinforcing steel in accordance with ICRI Technical Guideline No. 03730 "Guideline for Surface Preparation for the Repair of Deteriorated Concrete Resulting from Reinforcing Steel Corrosion."
2. For additional protection from future corrosion, coat the prepared reinforcing steel with Emaco® P24 rebar coating or install Emaco® Corr-Stops® CM galvanic anodes.

Mixing

WET PROCESS

1. Add 0.65 – 0.8 gallons (2.5 – 3.3 L) of potable water per 55 lb (25 kg) bag of Shotpatch® 21.
2. Mechanically mix using an appropriately sized mortar mixer. Pour approximately 90% of the water into the mixing container, then charge the mixer with the bagged material. Add the remaining mix water as required.
3. Mix for 3 – 5 minutes to reach a homogeneous consistency.

Application

1. Apply Shotpatch® 21 in accordance with ACI 506R "Guide to Shotcrete."
2. Apply Shotpatch® 21 while taking proper consideration for rebound and compaction around reinforcing steel. The successful application of Shotpatch® 21 depends primarily on the skill of the nozzleman.
3. When applying multiple lifts, scratch the preliminary lift before initial set. Apply the succeeding lift after the preliminary lift has reached final set. If the succeeding lift will not be immediately placed, keep the surface continually moist.
4. Cut off or level the application as required, matching the original concrete elevation.

5. In rapid-drying conditions (e.g., hot, dry, and windy weather) use Confilm® evaporation reducer.
6. Finish the final surface as required.

Curing

1. Proper curing is extremely important and should be conducted in accordance with ACI 308 "Standard Practice for Curing Concrete."
2. Apply a curing compound that complies with the moisture-retention requirements of ASTM C 309 or ASTM C 1315 or else moist cure for a minimum of 7 days.

For Best Performance

- Precondition these materials to approximately 70° F (21° C) for 24 hours before using.
- Protect repairs from direct sunlight, wind, and other conditions that could cause rapid drying of material.
- Water content should not exceed 0.9 gallons per 55 lb bag during application.
- Minimum application thickness is 3/8" (10 mm).
- Maximum application thickness is 6" (152 mm) per lift.
- Do not mix partial bags.
- Minimum ambient and surface temperatures should be 45° F (7° C) and rising at the time of application.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

SHOTPATCH® 21

Caution

Contains silica, crystalline quartz, Portland cement.

Risks

Product is alkaline on contact with water and may cause injury to skin or eyes. Ingestion or inhalation of dust may cause irritation. Contains small amount of free respirable quartz which has been listed as a suspected human carcinogen by NTP and IARC. Repeated or prolonged overexposure to free respirable quartz may cause silicosis or other serious and delayed lung injury.

Precautions

Avoid contact with skin, eyes and clothing. Prevent inhalation of dust. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Waste Disposal Method

This product when discarded or disposed of is not listed as a hazardous waste in federal regulations. Dispose of in a landfill in accordance with local regulations.

For additional information on personal protective equipment, first aid, and emergency procedures, refer to the product Material Safety Data Sheet (MSDS) on the job site or contact the company at the address or phone numbers given below.

Proposition 65

This product contains material listed by the State of California as known to cause cancer, birth defects or other reproductive harm.

VOC Content

0 g/L or 0 lbs/gal less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

**BASF Construction Chemicals, LLC –
Building Systems**

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517
Technical Service 800-243-6739



LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS,** and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND.** BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019337 8/07

Printed on recycled paper including 10% post-consumer fiber.

© 2007 BASF
Printed in U.S.A.