

PRODUCT DATA

3 03 01 00

Maintenance of
Concrete**CONCRESE[®] LIQUID LPL**

Concrete bonding adhesive with long pot life

Description

Concresive[®] Liquid LPL is a two-component 100% solids liquid epoxy bonding adhesive. It is designed for application in warm environments or applications requiring a long working time.

Yield

Smooth surfaces:
100 ft²/gallon (2.4 m²/L)

Rough surfaces:
50 – 75 ft²/gallon (1.2 – 1.8 m²/L)

Coverage rates are approximate. Actual coverage rate will depend on texture and porosity of concrete and application method employed.

Packaging

1 gallon (3.8 L) units

3 gallon (11.4 L) units

Shelf Life

2 years when properly stored

Storage

Store in sealed containers at temperatures between 50 and 90° F (10 and 32° C) in a clean, dry area.

Features

- Creamy high-build liquid
- Very long working time
- Moisture insensitive
- May be extended with properly graded sand

Benefits

- Single application
- Facilitates proper placement; ideal for warm environments
- Bonds to damp concrete surfaces
- More economical applications

Where to Use

APPLICATION

- Bonding fresh concrete to existing concrete
- Grouting bolts, dowels, and rebar into concrete, stone, and masonry
- Filling joints and voids in masonry
- Bonding concrete to dissimilar materials like steel and wood
- Coating rebar

LOCATION

- Interior or exterior

How to Apply**Surface Preparation**

CONCRETE

1. Substrate may be dry or damp, although dry surfaces product optimum results. New concrete must be fully cured (28 days minimum).
2. Remove grease, wax, oil contaminants, and curing compounds by scrubbing with an industrial-grade detergent or a degreasing compound.
3. Follow with mechanical cleaning (refer to ASTM D 4258). Remove weak, contaminated, or deteriorated concrete by shotblasting, bushhammering, gritblasting, scarifying, or other suitable mechanical means. Follow mechanical cleaning with vacuum cleaning (refer to ASTM D 4259).

STEEL

Remove dirt, grease, and oil with a suitable industrial-grade cleaning-and-degreasing compound (SSPC-SP-1). Remove rust and mill scale by gritblasting. Blast steel to white metal. Follow gritblasting with vacuuming or oil-free dry-air blast (refer to SSPC-SP-10 or NACE-2).

Mixing

1. The mix ratio is 2 (Parts A) to 1 (Part B). Mix only the amount of material usable before the pot life expires. Thoroughly stir each component before mixing.
2. Measure (ratio) each component carefully and then add Part B (hardener) to Part A (resin).
3. Mix Parts A and B using a low-speed drill (600 rpm) and mixing paddle (e.g., a Jiffy mixer). Carefully scrape the sides and bottom of the container while mixing. Keep the paddle below the surface of the material to avoid entrapping air. Proper mixing will take at least 3 – 5 minutes. Well-mixed material will be free of streaks or lumps.

Technical Data

Composition

Concrecive® Liquid LPL is a two-component 100% solids liquid epoxy.

Compliances

- ASTM C 881, Type II, Grade 2, Class C

Typical Properties

COMPONENT	PART A (Resin)	PART B (Hardener)
Form	Liquid	Liquid
Color	White	Black
Mixing ratio, by volume	2	1
Mixed color	Dark gray	

PROPERTY	VALUE		
	50° F (10° C)	77° F (25° C)	105° F (41° C)

Pot life

1 qt (946 ml)	4.5 hrs	75 min	30 min
1 gal (3.8 L)	3.9 hrs	70 min	25 min
5 gal (18.9 L)	2.5 hrs	60 min	20 min

Viscosity, cps

Resin	66,000	12,000	9,000
Hardener	1,150	350	110
Mixed	63,000	9,000	8,500

Thin film, open time	4 hrs	2 hrs	40 min
-----------------------------	-------	-------	--------

Thin film, days, full cure	14	7	3
-----------------------------------	----	---	---

Test Data¹

PROPERTY	RESULTS	TEST METHODS
Tensile strength, psi (MPa)	4,400 (30.4)	ASTM D 638
Elongation at break, %	1.49	ASTM D 638
Compressive yield strength, psi (MPa)	8,300 (57.3)	ASTM D 695
Compressive modulus, psi (MPa)	3.5 x 10 ⁶ (2.4 x 10 ⁵)	ASTM D 695
Heat deflection temperature, ° F (° C)	127 (53)	ASTM D 648
Slant shear strength, psi (MPa)	5,000 (34.5)	AASHTO T-237
Bond strength, damp-to-damp concrete	100% concrete failure	AASHTO T-237
Bond strength at 14 days, psi (MPa)	1,800 (12.4)	ASTM C 882
Flexural bond strength, psi (MPa)	570 (3.9)	ASTM C 293

¹Test temperature 77° F (25° C), cured 7 days.

Properties listed are typical and may be used as a guide for determining suitability for particular applications.

Application

GENERAL BONDING

Although this product will adhere to damp surfaces, dry surfaces produce the best results. When the surface is wet, remove free water by air blast or squeegee. Apply the bonding agent with a brush, paint roller, squeegee, conventional sprayer, or airless sprayer. The minimum bondline thickness should be 15 mils.

BONDING FRESH CONCRETE TO EXISTING CONCRETE

1. The new concrete being bonded should be a relatively low-slump mix.
2. When bonding concrete containing latex polymer admixtures, check compatibility either by installing a test patch and performing a pull-off test or by conducting a laboratory slant shear test (AASHTO T-237).
3. Apply the bonding agent as described in the General Bonding section above. Lightweight concrete may require a second coat if the first coat penetrates. Place fresh concrete within the open time or while the bonding agent is still tacky. Be careful when applying the fresh concrete not to damage the bonding layer.
4. For highly irregular surfaces sand may be used to extend this material. For proper application techniques refer to Appendix MB-17: Surface Preparation for Adhesives.

BOLT AND REBAR GROUTING

1. Holes may be cut by either rotary-percussion drilling, followed by air blow-out with oil-free compressed air, or diamond core boring, followed by water flush. The hole must be free of water before grouting. Where holes will be precast into the concrete, cast them undersized and drill them to fit.
2. The optimum hole size is 1/4" (6 mm) larger than the bar's; larger annular spaces are less desirable.
3. Pour a measured amount of bonding agent into the hole. Insert the bar, displacing the bonding agent, then secure the bar in the center of the hole. Remove excess bonding agent from around the hole before it hardens. Use pressure grouting for holes deeper than 2 ft (0.6 m).

Clean Up

Clean all tools and equipment immediately with xylene or mineral spirits. Cured material must be removed mechanically.

For Best Performance

- Precondition all components to 70° F for 24 hours before using.
- Application temperature range is 50 to 105° F (10 to 41° C).
- Do not add solvents or water to epoxy components.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

CONCRECIVE® LIQUID LPL PART A

Caution

Contains epoxy resin, 0-cresyl glycidyl ether.

Risks

May cause skin, eye and respiratory irritation. May cause dermatitis and allergic responses. Potential skin and/or respiratory sensitizer. Ingestion may cause irritation.

Precautions

Use only with adequate ventilation. Avoid contact with skin, eyes and clothing. Keep container closed when not in use. Wash thoroughly after handling. DO NOT take internally. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

For additional information on personal protective equipment, first aid, and emergency procedures, refer to the product Material Safety Data Sheet (MSDS) on the job site or contact the company at the address or phone numbers given below.

Proposition 65

This product contains materials listed by the state of California as known to cause cancer, birth defects, or reproductive harm.

VOC Content

0 g/L or 0 lbs/gal less water and exempt solvents when components are mixed and applied per Manufacturer's instructions.

CONCRECIVE® LIQUID LPL PART B

Danger-Corrosive:

Contains: Tall oil fatty acids, reaction products with tetraethylene pentamine; Tetraethylene pentamine; 2,4,6-Tris((dimethylamino)methyl)phenol.

Risks

Contact with skin or eyes may cause burns. Ingestion may cause irritation and burns of mouth, throat and stomach. Inhalation of vapors may cause irritation. May cause dermatitis and allergic responses. Potential skin and/or respiratory sensitizer. Repeated or prolonged contact with skin may cause sensitization. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL. Refer to Material Safety Data Sheet (MSDS) for effects of repeated overexposure.

Precautions

DO NOT get in eyes, on skin or clothing. Wash thoroughly after handling. Keep container closed. DO NOT take internally. Use only with adequate ventilation. DO NOT breathe vapors. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

For additional information on personal protective equipment, first aid, and emergency procedures, refer to the product Material Safety Data Sheet (MSDS) on the job site or contact the company at the address or phone numbers given below.

Proposition 65

This product does not contain materials listed by the state of California as known to cause cancer, birth defects, or reproductive harm.

VOC Content

0 g/L or 0 lbs/gal less water and exempt solvents when components are mixed and applied per BASF instructions.

**For medical emergencies only,
call ChemTrec (1-800-424-9300)**

**BASF Construction Chemicals, LLC –
Building Systems**

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517

Technical Service 800-243-6739



LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019340 7/07

Printed on recycled paper including 10% post-consumer fiber.

© 2007 BASF

Printed in U.S.A.